

ANSI/AWWA **C206-23**
(Revision of AWWA C206-17)

AWWA Standard

Field Welding of Steel Water Pipe

Effective date: Nov. 1, 2023.

First edition approved by Board of Directors Jan. 10, 1946.

This edition approved June 9, 2023.

Approved by American National Standards Institute July 27, 2023.




AWWA Standard

This document is an American Water Works Association (AWWA) standard. It is not a specification. AWWA standards describe minimum requirements and do not contain all of the engineering and administrative information normally contained in specifications. The AWWA standards usually contain options that must be evaluated by the user of the standard. Until each optional feature is specified by the user, the product or service is not fully defined. AWWA publication of a standard does not constitute endorsement of any product or product type, nor does AWWA test, certify, or approve any product. The use of AWWA standards is entirely voluntary. This standard does not supersede or take precedence over or displace any applicable law, regulation, or code of any governmental authority. AWWA standards are intended to represent a consensus of the water industry that the product described will provide satisfactory service. When AWWA revises or withdraws this standard, an official notice of action will be placed in the Official Notice section of *Journal AWWA*. The action becomes effective on the first day of the month following the month of *Journal AWWA* publication of the official notice.

American National Standard

An American National Standard implies a consensus of those substantially concerned with its scope and provisions. An American National Standard is intended as a guide to aid the manufacturer, the consumer, and the general public. The existence of an American National Standard does not in any respect preclude anyone, whether that person has approved the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard. American National Standards are subject to periodic review, and users are cautioned to obtain the latest editions. Producers of goods made in conformity with an American National Standard are encouraged to state on their own responsibility in advertising and promotional materials or on tags or labels that the goods are produced in conformity with particular American National Standards.

CAUTION NOTICE: The American National Standards Institute (ANSI) approval date on the front cover of this standard indicates completion of the ANSI approval process. This American National Standard may be revised or withdrawn at any time. ANSI procedures require that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of ANSI approval. Purchasers of American National Standards may receive current information on all standards by calling or writing the American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036; 212.642.4900; or emailing info@ansi.org.



ISBN-13, print: 978-1-64717-155-1

ISBN-13, electronic: 978-1-61300-684-9

DOI: <http://dx.doi.org/10.12999/AWWA.C206.23>

All rights reserved. No part of this publication may be reproduced or transmitted in any form or by any means, electronic or mechanical, including scanning, recording, or any information or retrieval system. Reproduction and commercial use of this material is prohibited, except with written permission from the publisher. Please send any requests or questions to permissions@awwa.org.

Copyright © 2023 by American Water Works Association
Printed in USA

Committee Personnel

The Steel Water Pipe Manufacturers Technical Advisory Committee (SWPMTAC) Task Group for updating ANSI/AWWA C206 had the following personnel at the time:

Bryan Hansen, *Chair*

H. Bardakjian, Manufacturer's Consultant, Glendale, Calif.

R.J. Card, Manufacturer's Consultant, Suwanee, Ga.

D. Dechant, Manufacturer's Consultant, Aurora, Colo.

D. Dunker, Thompson Pipe Group, Dallas, Tex.

J. Forni, Jifco Inc., Livermore, Calif.

B. Hansen, National Welding Corporation, Midvale, Utah

B.D. Keil, Northwest Pipe Company, Salt Lake City, Utah

J. Luka, American SpiralWeld Pipe Company, Columbia, S.C.

R. Mielke, Northwest Pipe Company, Raleigh, N.C.

R.N. Satyarthi, Baker Coupling Company, Los Angeles, Calif.

C. Sundberg, Victaulic, Issaquah, Wash.

M.A. Vanderbosch, CAB Inc., Oakwood, Ga.

The AWWA Standards Committee on Steel Pipe, which reviewed and approved this standard, had the following personnel at the time of approval:

John H. Bambei Jr., *Chair*

Robert J. Card, *Vice-Chair*

John L. Luka, *Secretary*

General Interest Members

S.A. Arnaout (*alternate*), Stantec, Dallas, Tex.

J.H. Bambei Jr., Bambei Engineering Services, Arvada, Colo.

R.J. Card, Lockwood, Andrews & Newnam, Suwanee, Ga.

R.L. Coffey, Consultant, Bend, Ore.

R.L. Gibson, Freese and Nichols Inc., Fort Worth, Tex.

M.D. Gossett, HDR, Denver, Colo.

M.B. Horsley (*alternate*), Horsley Engineering, Overland Park, Kans.

R. Issa, AECOM, McKinney, Tex.

C.H. Kirby (*alternate*), Lockwood, Andrews & Newnam Inc., Houston, Tex.

R.A. Kufaas, Norske Corrosion & Inspection Services Ltd., Abbotsford, B.C.
J.L. Mattson, Corrosion Control Technologies, Sandy, Utah
D.L. McPherson (*alternate*), HDR, Charlotte, N.C.
A. Murdock, Jacobs, Salt Lake City, Utah
R. Ortega, Aurora Technical Services, Houston, Tex.
E.S. Ralph (*liaison, nonvoting*), Standards Engineer Liaison, AWWA, Denver, Colo.
A.E. Romer (*alternate*), AECOM, Orange, Calif.
J.R. Snow, Stantec, Denver, Colo.
A.M. Stanton, Black & Veatch, Pasadena, Calif.
W.R. Whidden, Woolpert, Orlando, Fla.

Producer Members

H.H. Bardakjian, Consultant, Glendale, Calif.
D. Dechant, Dechant Infrastructure Service, Aurora, Colo.
D.W. Dunker, Thompson Pipe Group, Rialto, Calif.
B.D. Keil, Northwest Pipe Company, Salt Lake City, Utah
J.L. Luka, American SpiralWeld Pipe Company, Columbia, S.C.
R.D. Mielke (*alternate*), Northwest Pipe Company, Raleigh, N.C.
G.F. Ruchti (*alternate*), Consultant, Punta Gorda, Fla.
B.P. Simpson (*alternate*), American Cast Iron Pipe Company, Birmingham, Ala.
C.C. Sundberg, Victaulic, Issaquah, Wash.
R. Wu (*alternate*), Thompson Pipe Group, Grand Prairie, Tex.

User Members

L. Adams, US Bureau of Reclamation, Denver, Colo.
G.A. Andersen, New York City Bureau of Water Supply, Little Neck, N.Y.
B. Cheng, Metro Vancouver, Burnaby, B.C.
B. Fountain, San Diego County Water Authority, San Diego, Calif.
J. Fox, Tampa Bay Water, Clearwater, Fla.
J. Garcia (*alternate*), Metropolitan Water District, La Verne, Calif.
S. Hattan, Tarrant Regional Water District, Fort Worth, Tex.
M. Lobik, Springfield Water & Sewer, Springfield, Mass.
T. Peng, Metropolitan Water District, Los Angeles, Calif.
G. Ramon (*liaison, nonvoting*), Standards Council Liaison, Little Rock Water Reclamation Authority, Little Rock, Ark.
V. Scutelnicu, Los Angeles Department of Water and Power, Los Angeles, Calif.
M. Turney (*alternate*), Denver Water, Denver, Colo.

Contents

All AWWA standards follow the general format indicated subsequently. Some variations from this format may be found in a particular standard.

SEC.	PAGE	SEC.	PAGE
<i>Foreword</i>		4	Requirements
I	vii	4.1	Materials 4
I.A	vii	4.2	General Requirements 4
I.B	viii	4.3	Joint Types 5
I.C	viii	4.4	Qualification of Welding Procedures, Welders, and Welding Operators 7
II	ix	4.5	Welding Electrodes 8
III	ix	4.6	Welding Procedure Details 8
III.A	ix	4.7	Repair of Welds 11
		5	Verification
III.B	x	5.1	Inspection 12
IV	x	5.2	Testing 12
V	x	5.3	Rejection 14
<i>Standard</i>		6	Delivery
1		6.1	Marking 14
		6.2	Packaging and Shipping 15
1.1	1	6.3	Affidavit of Compliance 15
1.2	2		
1.3	2	Figures	
2		1	Fillet-Weld Size 9
		2	Look-Box for Vacuum Testing of Circumferential Weld Seams 14
3	3		

This page intentionally blank.

Foreword

This foreword is for information only and is not a part of ANSI/AWWA C206.*

I. Introduction.

I.A. *Background.* The provisions of this standard describe the requirements for welding steel water pipe joints in water transmission and distribution lines. The purchaser for each project is responsible for determining if any unusual circumstances related to the project require additional provisions that are not included in the standard.

The design of field-welded joints is not discussed in this standard. Useful information on this subject may be found in AWWA Manual M11, *Steel Pipe—A Guide for Design and Installation*,[†] and in *Useful Information on the Design of Plate Structures* (American Iron and Steel Institute[‡]).

In addition, manufacture and installation of field-welded joints are discussed in ANSI/AWWA C200, *Steel Water Pipe, 6 In. (150 mm) and Larger*, and ANSI/AWWA C604, *Installation of Buried Steel Water Pipe—4 In. (100 mm) and Larger*, respectively.

After the welded field joint has been completed, if the pipe has been coated or lined, the joint shall be coated and lined with a coating system compatible with that on the body of the pipe, in accordance with the requirements for field repairs stated in the appropriate AWWA coating or lining standard.

For lap-welded pipe with an inside diameter equal to or exceeding 48 in. (1,200 mm) and where the purchaser deems single welding to be acceptable, inside welding is recommended. Safety precautions shall be utilized in all pipe sizes, although when pipe with inside diameters less than 48 in. (1,200 mm) down to 27 in. (675 mm) is welded from the inside, additional safety precautions shall be observed. Interior welding on pipe diameters less than 27 in. (675 mm) is not recommended.

Pipe requiring inside welds with limited access should be supplied with typical 3-in. (75-mm) diameter weld lead pass holes at approximately 400-ft (122-m) centers to allow passage of welding leads to the joint location. Shorter distances between pass holes may be required, depending on actual project conditions. Pass holes in the pipe will permit shorter welding leads and thus avoid erratic voltage drops caused

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

† AWWA Manual M11. *Steel Pipe—A Guide for Design and Installation*. Denver, CO: AWWA.

‡ *Useful Information on the Design of Plate Structures*, Steel Plate Engineering Data, Vol. 2, American Iron and Steel Institute, 1101 17th Street, NW, Suite 1300, Washington, DC 20036.

by excessively long welding leads. The pass hole is fabricated using a weldable-grade inside-threaded pipe half-coupling or a flange with a short flange neck welded to a hole cut through the pipe wall. After using the pass hole, a weldable-grade plug shall be threaded into the opening and seal-welded to secure or a blind flange can be bolted over the flange opening.

I.B. *History.* This standard was first approved as tentative by AWWA in January 1946 and by the American Welding Society (AWS) in October 1945. It was advanced to standard status by AWWA in 1950 and by AWS in 1951. The joint AWWA–AWS activity continued through revisions in 1957 (AWWA C206-57, AWS D7.0-57) and 1962 (AWWA C206-62, AWS D7.0-62a). The joint committee was dissolved in 1971, and the standard was assigned to the AWWA Standards Committee on Steel Pipe. Subsequent editions of the standard were published in 1975, 1982, 1988, 1991, 1997, 2003, 2011, and 2017. This edition was approved by the AWWA Board of Directors on June 9, 2023.

I.C. *Acceptance.* In May 1985, the US Environmental Protection Agency (USEPA) entered into a cooperative agreement with a consortium led by NSF International (NSF) to develop voluntary third-party consensus standards and a certification program for direct and indirect drinking water additives. Other members of the original consortium included the Water Research Foundation (formerly AwwaRF) and the Conference of State Health and Environmental Managers (COSHEM). AWWA and the Association of State Drinking Water Administrators (ASDWA) joined later.

In the United States, authority to regulate products for use in, or in contact with, drinking water rests with individual states.[§] Local agencies may choose to impose requirements more stringent than those required by the state. To evaluate the health effects of products and drinking water additives from such products, state and local agencies may use various references, including

1. Specific policies of the state or local agency.
2. Four standards developed under the direction of NSF[¶]: NSF/ANSI/CAN^{**} 60, Drinking Water Treatment Chemicals—Health Effects; NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects; NSF/ANSI/CAN 372, Drinking Water System Components—Lead Content; and NSF/ANSI/CAN 600, Health Effects Evaluation and Criteria for Chemicals in Drinking Water.

[§] Persons outside the United States should contact the appropriate authority having jurisdiction.

[¶] NSF International, 789 North Dixboro Road, Ann Arbor, MI 48105.

^{**} Standards Council of Canada, 55 Metcalfe Street, Suite 600, Ottawa, ON K1P 6L5 Canada.

3. Other references, including AWWA standards, *Food Chemicals Codex*, *Water Chemicals Codex*,^{##} and other standards considered appropriate by the state or local agency.

Various certification organizations may be involved in certifying products in accordance with NSF/ANSI/CAN 61. Individual states or local agencies have authority to accept or accredit certification organizations within their jurisdiction. Accreditation of certification organizations may vary from jurisdiction to jurisdiction.

NSF/ANSI/CAN 600 (which formerly appeared in NSF/ANSI/CAN 60 and 61 as Annex A, “Toxicology Review and Evaluation Procedures”) does not stipulate a maximum allowable level (MAL) of a contaminant for substances not regulated by a USEPA final maximum contaminant level (MCL). The MALs of an unspecified list of “unregulated contaminants” are based on toxicity testing guidelines (noncarcinogens) and risk characterization methodology (carcinogens). Use of NSF/ANSI/CAN 600 procedures may not always be identical, depending on the certifier.

ANSI/AWWA C206 does not address additives requirements. Users of this standard should consult the appropriate state or local agency having jurisdiction in order to

1. Determine additives requirements, including applicable standards.
2. Determine the status of certifications by parties offering to certify products for contact with, or treatment of, drinking water.
3. Determine current information on product certification.

II. Special Issues. This standard has no applicable information for this section.

III. Use of This Standard. It is the responsibility of the user of an AWWA standard to determine that the products described in that standard are suitable for use in the particular application being considered.

III.A. *Purchaser Options and Alternatives.* The following information should be provided by the purchaser.

1. Standard used—that is, ANSI/AWWA C206, Field Welding of Steel Water Pipe, of latest revision.
2. Whether compliance with NSF/ANSI/CAN 61, Drinking Water System Components—Health Effects, is required.
3. Details of federal, state, provincial, territorial, and local requirements (Sec. 4.1.1).

^{##} Both publications available from National Academies Press, 500 Fifth Street, NW, Washington, DC 20001.

4. Provisions for alleviation of thermal stresses (Sec. 4.2.6).
5. Type of joint (Sec. 4.3).
6. Lap joint (Sec. 4.3.2).
7. Butt joint (Sec. 4.3.3).
8. Option regarding backing rings (Sec. 4.3.3.1).
9. Seal weld of butt straps to facilitate an air test (Sec. 4.3.4).
10. Notch tough weld criteria, if required; temperature of test; and test values (Sec. 4.6.10).
11. Weld inspection, if required (Sec. 5.1.3).
12. Testing methods, if required (Sec. 5.2).
13. Nondestructive testing of welded joints if substituted for hydrostatic tests (Sec. 5.2.2).
14. Affidavit of compliance (Sec. 6.3).

III.B. *Modification to Standard.* Any modification of the provisions, definitions, or terminology in this standard must be provided by the purchaser.

IV. Major Revisions. Major changes made to the standard in this revision include the following:

1. Additional wording was added to the Foreword to reference applicable standards for manufacture and installation of field-welded joints.
2. Updated Sec. I.C. Acceptance in the Foreword with the latest Standards Council language reflecting the addition of reference to NSF/ANSI/CAN 372 and NSF/ANSI/CAN 600.
3. In Section 3, the definition of *Seal weld* was added to provide clarification. The definitions for *potable water*, *reclaimed water*, and *wastewater* were also added based on the Standards Council boilerplate.
4. Updated Sec. 4.1 Materials with the latest Standards Council boilerplate language.
5. In Sec. 5.2.2.1, Testing field-butt joints with or without backing rings, ultrasonic testing was added as an acceptable verification method, and a note was added addressing ultrasonic testing of butt joints on material thickness less than $\frac{5}{16}$ in. (8 mm).

V. Comments. If you have any comments or questions about this standard, please call AWWA Engineering and Technical Services at 303.794.7711; write to the department at 6666 West Quincy Avenue, Denver, CO 80235-3098; or email at standards@awwa.org.



**American Water Works
Association**

Dedicated to the World's Most Vital Resource®

ANSI/AWWA C206-23
(Revision of AWWA C206-17)

AWWA Standard

Field Welding of Steel Water Pipe

SECTION 1: GENERAL

Sec. 1.1 Scope

This standard describes manual, semiautomatic, and automatic field welding by the metal arc-welding processes for steel water pipe manufactured in accordance with ANSI*/AWWA C200, Steel Water Pipe—6 In. (150 mm) and Larger. This standard describes field-performed full circumferential welding of three types of pipe joints: (1) lap joints, (2) butt joints, and (3) butt-strap joints. This standard also applies to other welding required in field fabrication and installation of specials and appurtenances. However, when possible, pipe fabrications and fittings should be performed by the manufacturer at a manufacturing facility. The design of field-welded joints is not covered within this standard.

This standard recognizes AWS[†] D1.1 as the supporting document. ANSI/AWWA C206 references subclauses within the AWS D1.1 clauses on Prequalification of WPSs, Qualification, Fabrication, Inspection, and Tubular Structures. When ANSI/AWWA C206 is silent regarding a requirement listed in AWS D1.1, such requirement is not required in ANSI/AWWA C206. Although AWS D1.1 supports ANSI/AWWA C206 in many sections, when there is a conflict between these documents then ANSI/AWWA C206 shall govern.

* American National Standards Institute, 25 West 43rd Street, Fourth Floor, New York, NY 10036.

† American Welding Society, 8669 NW 36 Street, No. 130 Miami, FL 33166.