

Please be aware that this PDF has been created from the original hardcopy document, which might not be in good condition and so the PDF might reflect this.

W/D DECEMBER '87 OBSOLETE + 1 AMD

BRITISH STANDARD 3351 : 1971 & AMD 1
UDC 665.6.026 : 621.64.03

SPECIFICATION FOR
PIPING SYSTEMS
FOR PETROLEUM REFINERIES
AND PETROCHEMICAL PLANTS



WITHDRAWN

BRITISH STANDARDS INSTITUTION

Gr 9

BS 3351 : 1971

SPECIFICATION FOR PIPING SYSTEMS FOR PETROLEUM REFINERIES AND PETROCHEMICAL PLANTS

BS 3351 : 1971



BRITISH STANDARDS INSTITUTION

Incorporated by Royal Charter

2 PARK STREET, LONDON, W1A 2BS

Telex: 266933

Telephone: 01-629 9000

	Page		Page
CHART			
1 and 1A. Flexibility factor k and stress intensification factor i	39	8.5 and 8.6 Set-in branches	70-71
FIGURES		8.7 and 8.8 Set-on branches with backing rings	72-73
1. Minimum Charpy-V impact requirements for carbon manganese steels in the as-welded condition and 3.5% Ni steels in the as-welded, or post-weld heat treated condition	55	8.9 Small branches	74
2. Minimum Charpy-V impact requirements for carbon manganese steels in the post-weld heat treated condition and unwelded materials	56	8.10 Unreinforced branches	75
3. Method for the determination of thickness (t) for the purpose of Figs. 1 and 2.	57	8.11 Reinforced branches	76
4 and 5. Definition of reinforcement areas	58	8.12 Reinforced branch connections	77
6.1 and 6.2 Preparations for butt-welded pipe joints	59-60	8.13 Triform reinforcement	78
6.3 Butt joints incorporating backing rings	61	9.1 Welding neck flange	79
6.4 Recessed joints with backing rings	62	9.2a 'Face and fillet' welded flange	80
6.5 to 6.7 Butt-welded joints in pipes	63-65	9.2b 'Face and back' welded flange	80
7. Socket welded connections	65	9.3a 'Bore and fillet' welded flange	81
8.1 to 8.4 Set-on branches	66-69	9.3b 'Bore and back' plate flange	81
		9.4a Slip-on (hubbed) flange	82
		9.4b Slip-on (plate) flange	82
		9.4e 'Fillet and back' welded flange	82
		10.1 and 10.2 Small branch connections	83-84
		10.3 Studded connections	85
		11.1 Gussetted bends	86
		12.1 to 12.3 Oxy-acetylene welded joints	87-89
		13.1 and 13.2 Joints in pipe in which the root runs are to be applied by the tungsten arc inert gas (T.I.G.) process	90-91

BRITISH STANDARD SPECIFICATION FOR

PIPING SYSTEMS

FOR PETROLEUM REFINERIES AND PETROCHEMICAL PLANTS

FOREWORD

This British Standard is one of a series published under the authority of the Petroleum Equipment Industry Standards Committee.

In the original edition, 1961, the provisions represented standards of design and construction basically similar to those laid down in the American standard code for petroleum refinery piping, ANSI B31.3. Since that time a number of significant differences from that code have been introduced in the light of experience and the technical developments. These differences appear, for example, in the provisions for the application of materials for low temperature service, the requirements for quality control and inspection of fusion welding, and the modifications to design stresses in accordance with currently accepted design stress criteria. Determination of these design stresses has been assisted by the publication of a series of British Standards for pipe, BS 3601-5, wherein are listed proof stress values at temperature and creep and stress to rupture properties.

In some respects, in particular the provisions for the treatment of piping flexibility, identity with the ANSI B31.3 code has been maintained, and acknowledgment is made to the American National Standards Institute for data used in the preparation of this standard.

The continuous development of materials and design makes it necessary for the provisions of this standard to be reviewed periodically, and in consequence it is desirable that experience in its application be conveyed to the Committee by users.

SPECIFICATION

1. GENERAL

1.1 SCOPE

This British Standard specifies minimum requirements and recommended practice for the selection and application of materials and components of piping systems in petroleum refineries and petrochemical plants and the design, fabrication, installation and testing of these systems.

Piping systems are interpreted as assemblies of pipe, valves, pipe fittings, flanges, bolting, gaskets and pipe supports.

This British Standard applies to piping systems within the plot limits of petroleum refineries, petrochemical plants, gas processing plants, refinery tank farms and marine discharge and loading points, and interconnecting lines between such facilities.

The standard is divided into seven sections, and full details of the scope of each section are given in the first clause of the section.

It does not apply to:

(1) piping systems within the boundaries of steam and power plants, for the design and construction of which British Standards or other accepted national codes are available;

(2) heater tubes, tube fittings and headers, including connections for piping;

(3) pressure vessels, heat exchangers, pumps, and other such equipment, including internal piping and connections for piping;

(4) piping located on refinery property which has been set aside for cross-country piping transmitting oil or gas through, to, or from the refinery;

(5) pilot plants and research equipment generally, except insofar as this standard may be considered as a guide.

1.2 DEFINITIONS

For the purposes of this British Standard the following definitions apply.

1.2.1 Process piping. All piping in a unit used in the processing of hydrocarbon and chemicals.

The term is taken to apply also to process lines directly interconnecting units, and to piping and fittings used to connect instruments to process piping and equipment.

1.2.2 Plot (battery) limits. The boundaries of an area occupied by a processing unit.

It is taken not only to apply to 'processing units' in the strict sense but also to other locations where it is felt that the restrictions and limitations specified in this standard for certain materials in connection with 'processing units' should be adhered to.

1.2.3 Non-hazardous service. A service in which failure would not, under normal circumstances, create a hazard to personnel and considered generally to be limited to neutral aqueous solutions and to the low pressure services of water, air, steam and inert gases.

1.2.4 Pipe making processes. The various methods of making pipe or tube, as follows.

1.2.4.1 Seamless process. A wrought steel tubular product made without a welded seam. It is manufactured by hot

working steel and, if necessary, by subsequently cold finishing the hot-worked tubular product.

1.2.4.2 Electric fusion welding process (EFW). Steel plate formed into tubular shape and the abutting edges joined by manual or automatic electric arc welding with or without the use of filler metal.

1.2.4.3 Spiral seam fusion welding process (SFW). Steel strip, sheet or plate rolled into tubular shape so as to form a helical seam around the circumference of the pipe. The helical seam is electric fusion welded by an automatic metal arc welding process (SFW), or by electric resistance welding process.

1.2.4.4 Electric resistance welding process (ERW). A length of steel strip formed into tubular shape and longitudinally resistance welded continuously by the passage of an electric current across the abutting edges without the addition of filler metal.

1.2.4.5 Electric induction welding process. A length of steel strip or plate formed into tubular shape and longitudinally induction welded continuously by the passage of an electric current across the abutting edges without the addition of filler metal.

1.2.4.6 Electric flash welding process. A length of steel strip or plate formed into tubular shape and longitudinally flash welded over the full length simultaneously by the passage of an electric current across the abutting edges without the addition of filler metal.

1.2.4.7 Butt-welding process (BW). A continuous steel strip passed through a tunnel furnace from which it emerges at forge welding temperature to enter a series of rolls which form it into a tube and forge weld the abutting edges together.

1.2.5 Design pressure. The value of pressure to be used in calculations of pipe thickness (see Section 5).

1.2.6 Design temperature. The temperature to be used to establish the appropriate value of design stress.

1.2.7 t for weld sizes. Where in the various figures at the end of this standard the sizes of weld are related to t , then t shall be taken to be the actual metal thickness of the section under consideration.

2. COMPONENTS

2.1 SCOPE OF SECTION 2

This section lists the standards with which the components should comply and gives an outline of requirements in the construction of piping systems.

2.2 GENERAL

2.2.1 The components used shall be in accordance with the relevant standards given in Table 1, except that this shall not preclude the use of other materials, designs or methods of manufacture which can be shown to meet the intent of this standard. In any such cases this shall be explicitly stated as a qualification of any claims that the piping system complies with the requirements of this standard.

2.2.2 Components shall be marked in accordance with the requirements of the relevant standards in Table 1. The marking shall permit the component to be properly identified.

TABLE 1. LIST OF STANDARDS

NOTE. Standards marked 'D' include dimensional requirements. For the purposes of this standard, the standards listed below are intended to apply only to the components listed in the second column.

Material	Component	Standard	Title		
Steel		FERROUS			
		BS 449	— The use of structural steel in building.		
		BS 1501-6: 1958	— Steels for use in the chemical, petroleum and allied industries.		
		BS 1510: 1958	— Steels for use in the chemical, petroleum and allied industries. (Low temperature supplementary requirements to BS 1501-1506).		
		Plates	BS 1501: Part 1: 1964	— Steels for fired and unfired pressure vessels. Plates. Part 1. Carbon and carbon manganese steels. Imperial units.	
			BS 1501: Part 2: 1970	— Steels for fired and unfired pressure vessels. Plates. Part 2. Alloy steels. Imperial units.	
		Forgings	BS 1503: 1969	— Steel for fired and unfired pressure vessels. Forgings.	
		Castings	BS 1504	— Carbon and alloy steel castings (not yet published; included in BS 1501-6: 1958).	
		Bars	BS 1506	— Carbon and alloy steel bars for bolting material (not yet published; included in BS 1501-6: 1958).	
		Pipe	BS 1600	D Dimensions of steel pipe for the petroleum industry. Part 1. Imperial units. Part 2. Metric units.	
			BS 3601*	— Steel pipes and tubes for pressure purposes. Carbon steel: ordinary duties.	
			BS 3602*	— Steel pipes and tubes for pressure purposes. Carbon steel: high duties.	
			BS 3603*	— Steel pipes and tubes for pressure purposes. Carbon and alloy steel: low-temperature duties.	
			BS 3604*	— Steel pipes and tubes for pressure purposes. Low and medium alloy steel.	
			BS 3605*	— Steel pipes and tubes for pressure purposes. Austenitic stainless steel.	
			API STD. 5L	D Line pipe.	
			API STD. 5LS	D Spiral-weld line pipe.	
			Valves	BS 1414	D Flanged and butt-welding end steel outside-screw-and-yoke wedge gate valves for the petroleum industry.
				BS 1570	D Flanged and butt-welding end steel plug valves for the petroleum industry (excluding well-head and flow-line valves).
		BS 1655		D Flanged automatic control valves for the petroleum industry (face-to-face dimensions).	
BS 1868	D Flanged steel check valves for the petroleum industry.				
BS 1873	D Flanged steel globe valves for the petroleum industry.				
BS 2080	D Summary of face-to-face dimensions of flanged ferrous valves for the petroleum industry.				
BS 2995	D Cast and forged steel wedge gate, globe, check and plug valves, screwed and socket-welding, sizes 2 in and smaller, for the petroleum industry.				
BS 3808	D Cast and forged steel flanged, screwed and socket-welding wedge gate valves (compact design), sizes 2 in and smaller, for the petroleum industry.				
BS 4460	D Steel ball valves for the petroleum industry.				
API STD. 6D	D Steel gate, plug, ball and check valves for pipe line service.				

* See 2.3.1.